

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES


Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



Europäisches Patentamt
European Patent Office
Office européen des brevets



Publication number: **0 458 343 A1**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 91108381.4

(51) Int. Cl.⁵: D02G 3/12, D02G 3/44,
A41D 31/00, A41D 13/10

(22) Date of filing: 23.05.91

(23) Priority: 25.05.90 US 529241

(24) Date of publication of application:
27.11.91 Bulletin 91/48

(25) Designated Contracting States:
DE FR GB IT NL

(71) Applicant: BETTCHER INDUSTRIES, INC.
State Road 60 at Ohio Turnpike
Birmingham Ohio 44816(US)

(72) Inventor: Hummel, Joseph
471 Oaknoll Drive
Amherst, Ohio 44001(US)

(74) Representative: Baillie, Iain Cameron et al
c/o Ladas & Parry Isartorplatz 5
W-8000 München 2(DE)

(54) Knittable yarn and safety apparel.

(57) Yarn and a knitted safety glove or other article made of the yarn (13), which has a core (10) of at least one strand (20) of high strength liquid crystal polymer fiber such as Vectran HS fiber surrounded by one (12) or two (12,14) wrappings of high strength synthetic fiber, preferably high strength liquid crystal polymer fiber such as Vectran HS fiber or high strength aramid fiber, or high strength stretched

polyethylene fiber, or a combination of high strength fibers. One embodiment of the yarn includes a wire strand in the core. In one embodiment the fiber core strand (30) is of 200 to 1500 denier and has one to fifty filaments of 4 to 500 denier. In another embodiment, a second high strength synthetic core strand is included.




Fig. 1

EP 0 458 343 A1

preferred yarn construction has not only high resistance to cutting, but also good wear qualities and comfort, does not take a set during use, is non-abrasive, provides a good appearance, and is cleanable and long wearing.

The above and other features and advantages of the invention will become more apparent from the detailed description that follows.

Brief Description of the Drawings

Figure 1 is a fragmentary, diagrammatic, view of a yarn embodying the present invention;

Figure 2 is a fragmentary, diagrammatic, view of a second yarn embodying the present invention;

Figure 3 is a fragmentary, diagrammatic, view of a third yarn embodying the present invention; and

Figure 4 is a diagrammatic view of an article of apparel, i.e., a knitted glove, made of yarn embodying the present invention, such as the yarn shown in Figures 1, 2 and 3.

Best Mode for Carrying Out the Invention

The depicted glove A is exemplary of a safety article of apparel embodying the present invention and is a safety or protective glove suitable to be worn by operatives in the food processing and other industries where sharp instruments or articles, such as knives, or material having sharp edges, for example, sheet metal, glass and the like, are handled, and is made of a composite multistrand yarn B, C or D constructed in accordance with the present invention. The glove A has the usual finger and thumb stalls 4, 6 respectively, and a wrist part 8 incorporating an elastic thread or yarn. The glove is made using conventional methods and glove knitting machinery.

The yarn B employed in the glove A comprises a core part 10 and two windings 12, 14 of synthetic fiber wound thereon in opposite directions one on top of the other. The fact that the wrappings 12, 14 are in different directions balances the forces incident to the wrappings so the yarn has no unusual twist or tendency to coil and assists in holding the wrappings in place on the core 10. The windings are between four and twenty turns per inch and preferably about eight to twelve turns per inch. The core part 10 of the yarn B comprises two strands of annealed stainless steel wire 16 and 18, and one strand 20 of Vectran HS fiber, marketed by Hoechst Celanese Corporation. In another preferred embodiment, only one strand of annealed wire identical to the strand 16 is provided in the core.

The core structure 10 is designed to provide cut resistance, knittability, flexibility and life to the yarn; and the wrappings 12, 14 retain the core and

create body. One or both of the wrappings 10, 12 are of high strength synthetic fiber to contribute significantly to the cut resistance of the yarn.

The stainless steel wire 16 of the core part of the yarn B has a diameter of about 0.003 inch, 0.076mm. Stainless steel wire of the size mentioned, of 304 stainless steel, fully annealed, which has a tensile strength of about 110,000 to 135,000 pounds per square inch, is believed to have optimum flexibility and life.

The strand of synthetic fiber 20 in the core 10 of the yarn B is a high strength relatively non-stretchable multifilament synthetic fiber of Vectran HS having a tensile strength greater than that of the wire. The Vectran HS liquid crystal polymer fiber has an initial tensile modulus of at least about 600 grams per denier. It has a tenacity (tensile strength at break) of about 20 to 25 grams per denier and its elongation at break is about 2.2 to 2.5 percent. The size of the strand 20 is 900 denier, but other sizes are suitable, from about 200 to about 1,500 denier, more preferably from about 500 to about 1200 denier, and most preferably from about 900 to about 1200 denier.

The first or inner wrapping 12 on the core 10 of the yarn B is a high strength synthetic fiber, preferably a multifilament high strength fiber material, such as Vectran HS is used for the strand 20. Because Vectran HS fiber material has good abrasion resistance and heat resistance along with its cut resistance, it is advantageously used for the outer wrapping 14 as well as for the inner wrapping 12. Thus, in the embodiment shown, the outer wrapping 14 of the yarn B is identical to the inner wrapping 12, except wrapped in the opposite direction. The use of a single high strength fiber material for both wrappings 12 and 14 simplifies inventory and processing procedures and gives improved cut and abrasion resistance over the use of two aramid wrappings or an aramid inner wrapping and a nylon outer wrapping and better heat resistance over the use of two high strength stretched polyethylene wrappings or an inner high strength stretched polyethylene inner wrapping and a nylon outer wrapping. While a polyester outer wrap may be used in place of the outer Vectran HS wrap, a reduction in cut resistance will result. Each wrapping 12 and 14 is of a denier of from about 200 to about 1500, more preferably from about 200 to about 1000, and most preferably from about 200 to about 800. Preferably each wrapping is about 200 denier when the yarn is used for a glove knitted with two strands of the yarn (i.e., two strands of yarn are threaded concurrently through a knitting needle), or when the yarn is used for a lighter weight glove having greater flexibility and comfort. For a glove or protective garment knit from a single strand of yarn and also having very high cut resis-

high strength liquid crystal polymer fibers, such as Vectran HS fibers, provide increased cut resistance over yarn that utilizes comparable quantities of aramid fiber and provide improved abrasion resistance. Wash and dry tests show it has substantially less shrinkage than high strength stretched polyethylene.



While the yarn of the invention has been described and shown incorporated into a knit safety glove, it is to be understood that the yarn of the present invention can be used to make other fabrics and articles of apparel, safety or otherwise, such as wrist guards, protective sleeves, gaiters, safety aprons, etc. for use in the meat processing and other industries.



While variations in certain of the materials and sizes of the strands employed in preferred embodiments of the invention herein described can be made, the preferred embodiments of the yarn of the present invention are believed to produce the optimum balance between strength, resistance to cutting, resistance to heat, appearance, comfort, knittability, wearability, cleanability, and cost.

From the foregoing description of preferred embodiments of the invention it will be apparent that the advantages of the invention heretofore enumerated and others have been accomplished and that there have been provided an improved knittable yarn and safety articles of apparel made therewith having superior qualities. While preferred embodiments of the invention have been described in considerable detail, various modifications or alterations may be made therein without departing from the spirit or scope of the invention set forth in the appended claims.

Claims

1. In a cut-resistant yarn suitable for machine knitting including a core having high strength synthetic fiber and a wrapping of synthetic fiber about the core, the wrapping having a tenacity greater than 10 grams per denier; the improvement wherein the said core fiber is a high strength liquid crystal polymer having an initial tensile modulus of at least 600 grams per denier and a denier of about 200 to 1500.
2. A cut-resistant yarn as set forth in Claim 1 further including an additional wrapping of synthetic fiber, the wrapping strands having a denier of about 200 to 1000 and a tensile strength greater than 110,000 pounds per square inch and wherein the core fiber comprises no more than 50 filaments.
3. A cut-resistant yarn as set forth in Claim 1 having three wrappings, one being a high strength aramid fiber having a denier of about 200 to 1500, another being a high strength stretched polyethylene fiber having a denier of about 200 to 1500, and an outer wrapping of a synthetic fiber having a denier of about 200 to 1000, and wherein the overall diameter of the yarn is no greater than 0.05 inch.
4. A cut-resistant yarn as set forth in claim 1 wherein the core includes a flexible metal wire having a diameter between 0.051 millimeters to 0.254 millimeters the improvement further characterized in that said wrapping of synthetic fiber is a high strength liquid crystal polymer fiber having a denier of about 200 to 1200.
5. A cut-resistant yarn as set forth in Claim 4 further including a second wrapping of high strength liquid crystal polymer fiber and wherein both wrappings have an initial tensile modulus of at least 600 grams per denier.
6. A cut-resistant glove as set forth in Claim 4 wherein the core comprises at least two and no more than six strands of fully annealed stainless steel wire having a diameter of from about 0.051 millimeter to about 0.152 millimeter.
7. A cut-resistant glove as set forth in Claim 4 wherein the overall diameter of the yarn is no greater than 1.27 millimeter.
8. A cut-resistant yarn as set forth in claim 4 wherein the high strength liquid crystal polymer fiber of the core has an initial tensile modulus of at least 600 grams per denier and a denier of about 900 to 1200, and there are two wrappings of synthetic fiber wound about the core, one wrapping being a high strength liquid crystal polymer fiber having an initial tensile modulus of at least 600 grams per denier and a denier of between about 200 to 800, and the overall diameter of the yarn being no greater than 1.27 millimeters.
9. A cut-resistant article of apparel knitted from the yarn as set forth in any one of Claims 1-8.
10. A cut-resistant glove knitted from the yarn as set forth in any of Claims 1-8.







European
Patent Office

EUROPEAN SEARCH REPORT

Application Number

EP 91. 10 8381

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	US-A-4 912 781 (ROBINS ET AL) * column 3, line 23 - line 46; claims 3,5,8,9; figures 2-4 *	1,2,7-10	D 02 G 3/12 D 02 G 3/44 A 41 D 31/00 A 41 D 13/10
A,D	US-A-4 470 251 (BETTCHER) * column 2, line 44 - column 3, line 34 * * column 3, line 49 - column 4, line 48; figures 1-3 *	1-4,6-10	
A,D	US-A-4 384 449 (BYRNES SR ET AL) * claims 1-5,11-31; figures 1,2 *	1-10	
A,D	US-A-4 413 110 (KAVESH ET AL) * abstract *	1-3	
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			D 02 G A 41 D D 07 B
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of search 04 September 91	Examiner TAMME H.-M.N.
<div>CATEGORY OF CITED DOCUMENTS</div> <div>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention</div> <div>E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document</div>			